

AL World Standard

Category	China(GB)		USA	ENGLAND	JIS	FRANCE	GERMANY	RUSSIA
	Old Version	New Version	ASTM	BS	JIS	NF	DIN	ГОСТ
commercial-purity aluminium	L1		1070		A1070			A00
	L2		1060		A1060			A0
	LB2	1A50	1050	1050(1B)	1050	1050A	A199.50	A5
	L5-1		1100	3L54	A1100		A199.0	
	L5		1200	1C	A1200		A199	
	LG1	1A85	1080	1A	A1080		AL99.8	AB2
	LG2	1A90	1090		IN90		AL99.9	AB1
	LG3	1A93						
	—	1A95						A95
	LG4	1A97	1197				A199.98R	A97
	LG5	1A99	1199	S1	IN99		A199.99R	A99
	LF2	5A02	5052	NS4	5052	5052	A1Mg2.5	Amg
	LF3	5A03	5154	NS5				AMg3
	LF4	5A04	5083					
	LF5	5A05	5046	NB6	5056		A1Mg5	AMg5V
	LF5-1	5A06	5056					
	LF7							
	LF8							
	LF9							
	LF10	5B05						
	LF11							
LF12	5A12							
LF13	5A13							
LF14	5B06							
LF15	5A01							
LF16	5A30	5456	NG61	5556	5957			
LF21	3A21	3003						
LF33	5A33							
dural	LY1	2A01	2217		2217	2217	AlCu2.5Mg0.5	D18
	LY2	2A02						
	LY4	2A04						
	LY6	2A06						
	LY8	2B11						
	LY9	2B12						
	LY10	2A10						
	LY11	2A11	2017	HF15	2017	2017S	AlCuMg1	D1
	LY12	2A12	2024		2024	2024	AlCuMg2	D16AVTV
	LY13	2A13						

	LY16	2A16	2319					
Category	China(GB)		USA	ENGLAND	JIS	FRANCE	GERMANY	RUSSIA
	Old Version	New Version	ASTM	BS	JIS	NF	DIN	ГОСТ
dural	LY17	2A17						
	LY19		2219					
	LY20	2A20						
Forging Al	LD2	6A02	6165					
	LD7		2618					
	LD8	2A80			2N01			AK4
	LD9	2A90	2018		2018			AK2
	LD10	2A14	2014		2014	2014	AlCuSiMn	AK8
	LD11		4032					
	LD30		6061					
	LD31		6063					
Ultraduralumin	LC3	7A03	7174					
	LC4	7A04						
	LC5	7A05	7076					
	LC9	7A09	7075		7075	7075	AlZnMgCu1.5	V95P
	LC10	7A10	7079					
	LC12		7003					
	LC15	7A15						
	LC19	7A19						
	LC52	7A52						
Cast aluminium alloy		ZAlSi7Mn	356.2	LM25	AC4C		G-AlSi7Mg	
		ZAlSi12	413.2	LM6	AC3A	A-S12-Y4	G-Al12	AL2
		ZAlSi5Cu1Mg	355.2					AL5
		ZAlSi2Cu2Mg1	413.0		AC8A		G-Al12(Cu)	
		ZAlCu5Mn						AL19
		ZAlCu5MnCdVA	201.0					
		ZAlMg10	520.2	LM10		AG11	G-AlMg10	AL8
		ZAlMg5Si					G-AlMg5Si	AL13
Special aluminium alloy	LT1		4043	N21	A4043			
	LT17		4047	N2	A4047			